



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶: C04B 24/26, C08F 8/30, 8/48	A2	(11) International Publication Number: WO 95/09821 (43) International Publication Date: 13 April 1995 (13.04.95)
(21) International Application Number: PCT/US94/10134 (22) International Filing Date: 13 September 1994 (13.09.94) (30) Priority Data: 08/128,939 29 September 1993 (29.09.93) US 08/299,028 6 September 1994 (06.09.94) US (71) Applicant: W.R. GRACE & CO.-CONN. [US/US]; 1114 Avenue of the Americas, New York, NY 10035 (US). (72) Inventors: ARFAEL, Ahmad; 72 Stonegate Road, Chelmsford, MA 01824-4153 (US). DARWIN, David, Charles; 9009 Blue Pool, Columbia, MD 21045 (US). GARTNER, Ellis, Martin; 1105 Tanley Road, Silver Spring, MD 20904 (US). CHUN, Byong-Wa; 3-22-6 Kirigaoka #306, Midori-ku, Yokohama, Kanagawa 227 (JP). KOYATA, Hideo; 4-2-1 Ryokuen #2-105, Izumi-ku, Yokohama, Kanagawa 245 (JP). KUO, Lawrence, Lu; 8592 Dark Hawk Circle, Columbia, MD 21045 (US). (74) Agent: TROFFKIN, Howard, J.; W.R. Grace & Co.-Conn., 7379 Route 32, Columbia, MD 21044 (US).		(81) Designated States: AM, AT, AU, BB, BG, BR, BY, CA, CH, CN, CZ, DE, DK, EE, ES, FI, GB, GE, HU, JP, KE, KG, KP, KR, KZ, LK, LR, LT, LU, LV, MD, MG, MN, MW, NL, NO, NZ, PL, PT, RO, RU, SD, SE, SI, SK, TJ, TT, UA, UZ, VN, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG), ARIPO patent (KE, MW, SD). Published <i>Without international search report and to be republished upon receipt of that report.</i>
(54) Title: IMPROVED CEMENT ADMIXTURE PRODUCT HAVING IMPROVED RHEOLOGICAL PROPERTIES AND PROCESS OF FORMING SAME (57) Abstract The present invention is directed to an imidized polycarboxylic acid polymer useful as a cement admixture, to improved cement compositions containing said polymer and to a process of forming the same.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo			SE	Sweden
CH	Switzerland	KR	Republic of Korea	SI	Slovenia
CI	Côte d'Ivoire	KZ	Kazakhstan	SK	Slovakia
CM	Cameroon	LI	Liechtenstein	SN	Senegal
CN	China	LK	Sri Lanka	TD	Chad
CS	Czechoslovakia	LU	Luxembourg	TG	Togo
CZ	Czech Republic	LV	Latvia	TJ	Tajikistan
DE	Germany	MC	Monaco	TT	Trinidad and Tobago
DK	Denmark	MD	Republic of Moldova	UA	Ukraine
ES	Spain	MG	Madagascar	US	United States of America
FI	Finland	ML	Mali	UZ	Uzbekistan
FR	France	MN	Mongolia	VN	Viet Nam
GA	Gabon				

**Improved Cement Admixture Product
Having Improved Rheological Properties
and Process of Forming Same**

BACKGROUND OF THE INVENTION

5 The present invention is directed to a hydraulic
cement admixture, improved cement compositions containing
said admixture and to processes of forming said admixture
product. Specifically, the present invention relates to
10 a hydraulic cement admixture product composed of certain
derivatives of polyacrylic acid polymers, as fully
described below, which are capable of imparting high
flowability to cement compositions and of causing the
treated compositions to retain high flowability over a
sustained period of time without imparting a significant
15 delay in the initial set time.

 Although increased flowability can be attained by
using large dosages of water in a hydrating cement
composition, it is well known that the resultant cement
based structure will have poor compressive strength and
20 related properties. Various additives have been proposed
to increase the flowability (known as "slump") of cement
composition, such as mortar and concrete compositions,
without increasing the water content of the initially
formed composition. Such additives have been classified
25 as "cement superplasticizers" and include, for example,
compounds, such as naphthalene sulfonate-formaldehyde
condensates, lignin sulfonates and the like.

 More recently, copolymers of alkenyl ethers and
acrylic acid or maleic anhydride, and derivatives
30 thereof, have been proposed as agents suitable to enhance
slump [Japanese Patent Publication (Kokai) Nos 285140/88
and 163108/90]. Further, copolymers formed from the
copolymerization of hydroxy-terminated allylether and
maleic anhydride or the allylether and a salt, ester or

amide derivative of maleic anhydride such as disclosed in U. S. 4,471,100 have been proposed as cement admixtures capable of enhancing slump.

5 In each of the above instances, the proposed cement admixture material when used in a cement composition does not provide the desired combination of properties or only provide them in low degrees. For example, esterified acrylate copolymers, while providing good slump enhancement, also causes the treated cement composition
10 to exhibit excessive set retardation.

Prior acrylic acid polymer derivatives have been formed by first reacting acrylic acid with the derivative forming amine and then subjecting the vinyl amide monomer to vinyl polymerization conditions. Such polymerization
15 is difficult to control, provides product of a wide distribution of molecular weight and does not permit desired imide moieties to be present in the resultant polymer.

20 It is highly desired to have an admixture which is capable of imparting to a treated cement composition, a high degree of slump, of preventing a decrease in slump (decrease in flowability) over a sustained period of time, and at the same time, not causing the composition to exhibit excessive set retardation.

25 It is further highly desired to provide a simple process for forming the desired polymeric admixture.


SUMMARY OF THE INVENTION

30 The present invention is directed to the formation of imidized derivatives of carboxylic acid group containing polymers wherein the carboxyl groups are positioned alpha-beta and/or alpha-gamma with respect to

- 3 -

one another, such as polymer products disclosed in copending U. S. application Serial No. 08/128,939.

The present invention is directed to an improved hydraulic cement admixture product, hydraulic cement composition containing such product, and to a process for forming said product. The admixture product can be represented by the general formula:



wherein each R independently represents hydrogen atom or a methyl (CH₃-) group; R' represents a hydrogen atom or a C₂-C₁₀ (preferably C₂-C₄) oxyalkylene group (BO) or a plurality (1-200, preferably from 1 to 70) of said groups which is terminated with a C₁-C₁₀ alkyl group (R'') or mixtures thereof; A represents a hydrogen atom, a C₁-C₁₀ alkyl group, R' or an alkali or alkaline earth metal or ammonium cation or a mixture thereof; NR''' represents a radical group derived from a cyclic ring compound having at least one secondary nitrogen as part of the ring, and a, b, c, d and e each represent molar percentages of the polymer's structure such that a is an integer of from about 50 to 90; the sum of c plus d is at least about 2 to a value of [100 - (a+b)] and is preferably from 2 to 10; e is a value of 0 to about 10; and b is not more than [100 - (a+c+d+e)].

The process of forming the above admixture product comprises reacting a preformed polymer having carboxylic acid groups with an amine or hydroxy terminated

- 4 -

oxyalkylene compound at elevated temperature with continuous withdrawal of water, as fully described below.

DETAILED DESCRIPTION OF THE INVENTION

5 The present invention is directed to an improved cement admixture product and to cement compositions formed with said product and to a process of forming said product. The presently described improved cement admixture product has been unexpectedly found to provide
10 a cement composition, such as mortar or concrete, having high flowability over an extended period of time without imparting a significant delay in the initial set time of the composition. Thus the presently achieved cement compositions are capable of being readily formed into a desired shape, having substantial self-leveling
15 properties and can be worked over an extended period from commencement of hydration. At the same time, the presently achieved cement compositions do not exhibit extensive delay in set and, therefore, do not delay the timetable for forming the desired structure.


20 The cement admixture product of the present invention is composed of an imidized acrylic polymer, as fully described below, alone or as a uniform mixture with hydraulic cement. The cement can be selected from any conventional hydraulic cements such as, for example,
25 normal portland cement (meeting the requirements of ASTM C-150), high early strength portland cement, ultra high early strength portland cement, blast-furnace slag cement, fly-ash cement, blended portland cements, calcium aluminate cements, calcium sulfate cements, magnesium
30 phosphate cements and the like.

 The subject polymers are imidized acrylic polymers.

- 5 -

The term "acrylic polymer", as used herein and in the appended claims can be selected from homopolymer or copolymer of acrylic acid, methacrylic acid, their alkali metal and ammonium salts as well as their C₁-C₃₀ alkyl esters and/or polymers formed from other monomeric compounds having ethylenic unsaturation suitable for vinyl polymerization and providing alpha-beta or alpha-gamma positioned carboxylic acid groups, such as maleic anhydride, maleic acid and salts thereof. In addition, the acrylic polymer reactant and the resultant imidized acrylic polymer may contain units derived from other singly and doubly ethylenically unsaturated monomers, such as styrene, alpha-methylstyrene, sulfonated styrene, acrylonitrile, butadiene and the like. Such other ethylenically unsaturated monomer derived units, when present, can be present in the subject polymer in amount of up to about 20 (preferably, up to about 10) weight percent of the total polymer provided that the resultant imidized acrylic polymer is water soluble. Such other ethylenically unsaturated monomer derived units, although not shown in the structural formula exemplifying the subject imidized acrylic polymer, are contemplated to optionally be a part thereof.

The imidized acrylic polymer found useful in the present invention has a structural formula (I) of:



- 6 -

wherein each R independently represents hydrogen atom or a methyl (CH_3 -) group; R' represents a hydrogen atom or a C_2 - C_{10} (preferably C_2 - C_4) oxyalkylene group (BO) or a plurality (1-200, preferably from 1 to 70) of said groups which is terminated with a C_1 - C_{10} alkyl group (R'') or mixtures thereof; A represents a hydrogen atom, a C_1 - C_{10} alkyl group, R' or an alkali or alkaline earth metal or ammonium cation or a mixture thereof; NR''' represents a radical group derived from a heterocyclic ring compound having at least one secondary nitrogen as part thereof; and a, b, c, d and e represent molar percentages of the polymer's structure such that a is an integer of from about 50 to 90; the sum of c plus d is at least about 2 to a value of $[100 - (a + b)]$ and is preferably from 2 to 10; e is a value of 0 to about 10; and b is not more than $[100 - (a+c+d+e)]$.

The preferred imidized polymer is represented by the above formula in which A is a hydrogen atom or an alkali metal cation; R' is at least from 50 to 90 weight percent of the polymer and comprises polyoxyethylene or polyoxypropylene units or mixtures thereof.

Further, a preferred imidized acrylic polymer of the present invention has a portion of the molar percentage of the "a" monomeric units composed of units wherein A represents R' and the remainder of A represents hydrogen or alkali metal ion. The amount of "a" units wherein A represents R' can be from 2 to 30 percent of the total "a" molar units. Still further, it is preferred that "a" has a numerical value of from 60 - 70; and the sum of "c" plus "d" is a numerical value of at least 3 to a value of $[100 - (a+b)]$.


- 7 -

The present imidized acrylic polymer is formed by a process of reacting a preformed acrylic polymer with a primary amine containing a compound, as fully described herein below. The reactants can further include
5 secondary amine-containing heterocyclic compounds and/or hydroxy terminated oxyalkylene compounds. The use of a preformed acrylic polymer, as required by the present process, provides a resultant cement admixture product of well controlled molecular weight and of the desired
10 constituents.

The acrylic polymer reactant useful herein are low molecular weight polymers which are soluble in polar solvents such as water. They should have a number average molecular weight of from about 1,000 to 100,000,
15 preferably from about 1,500 to 20,000. The acrylic polymer reactants of both homopolymer and copolymer character are formed by conventional free radical polymerization and are commercially available.

The imidized acrylic polymer is formed by reacting
20 an acrylic polymer with ammonia or an alkoxylated amine. When an alkoxylated amine (preferred) is used as a reactant, the imidization may be carried out neat, as the acrylic polymers are soluble in such amines.

The amine reactant useful in forming the desired
25 imidized acrylic polymer can be selected from ammonia or an alkyl-terminated alkoxy amine represented by the formula:



in which BO represents a C₂-C₁₀ (preferably a C₂-C₄)
30 oxyalkylene group in which O represents an oxygen atom and B represents a C₂-C₁₀ (preferably C₂-C₄) alkylene group

or mixture; and R" represents a C₁-C₁₀ (preferably C₁-C₄) alkyl group and n is an integer selected from 1 to 200 preferably from 10 to 120.

The amine reactant is normally used in from about 5 to 90 mol percent and preferably from 10 to 20 mol percent based on the acrylic acid units present in the acrylic polymer.

In addition to the alkoxyated amine reactant, the acrylic polymer can be further formed with hydroxy terminated oxyalkylenes represented by the formula



wherein BO, R" and n are defined in formula II above.

The hydroxy terminated compound, when present, is normally used in a mole ratio of amine terminated to hydroxy terminated compound of from about 0.5 to 1.5.

The compounds of formula III react with the carboxyl groups of the acrylic polymer to provide a portion of the A constituent of the imidized acrylic polymer product of formula I.

The subject polymer can also contain small amounts of derivatives of compounds II and III in which R" of compound II is a primary amino group and R" of compound III is a hydroxyl group. Such derivatives have the formula Z(BO)_nZ where each Z is a primary amino or a hydroxyl group. The resultant polymer provides extended high slump properties. These derivatives may be present in up to 8 percent, preferably up to 5% provided that the resultant product is water soluble.

Another class of reactant which may optionally be used in forming the subject imidized acrylic polymer of the present invention are heterocyclic compounds having a secondary amine as part of the ring structure as

- 9 -

represented by a formula NHR''' wherein R''' represents two alkyl groups each having one to 10 carbon atoms or 4 to 7 member ring with the secondary nitrogen atom. The ring may contain other hetero atoms such as nitrogen and oxygen as part of the ring in addition to the secondary nitrogen atom. Such compounds include, for example, pyrrolidine, pyrroline, pyrazolidine, imidazolidine, piperidine, indoline, morpholine and the like. These heterocyclic reactants provide the formation of polymer units of formula I providing units of "e" moles. The inclusion of such heterocyclic moieties is believed to provide a resultant polymer product with still further capability to enhance (reduce) the set retardation and air entraining properties of the treated cement.

The acrylic polymer and amine reactants alone or further combined with a hydroxy terminated reactant and/or a heterocyclic reactant form the desired imidized acrylic polymer by heating the reactants either in an aqueous solution or neat at elevated temperatures of from about 60°C to 250°C and most preferably from 100°C to 225°C. The reaction is carried out under ambient pressure or, under a pressure lower than ambient pressure. Further, when the reaction is carried out under ambient or substantially ambient pressure it is preferred to conduct the reaction while passing air or nitrogen gas over the liquid reaction medium or by bubbling the gas through the medium to remove water and other low molecular weight by-products from the reaction zone.

The reactants are contacted with each other under elevated temperature. Temperatures of greater than about 150°C (preferably between 150 and 225°C) are required when the reactants are contacted in the absence of a catalyst, such as described below. When a catalyst is

- 10 -

employed the reaction temperature required can be substantially reduced. Catalyst enhanced reaction normally can be carried out at temperatures of at least about 60°C, preferably from about 100 to 140°C. The
5 desired imidization occurs more readily when using higher reaction temperatures. Therefore, when optional reactants are also employed it is desired to carry out the reaction as a two step process by first heating the reactants to greater than 150°C for a period of time to
10 cause the primary amine reactant to substantially combine with the polymer carboxyl groups and then to lower the reaction temperature to 75 - 140°C (preferably 100° to 130°C), introduce a catalyst, as described below, and maintain the lower temperature for a period to permit
15 substantial completion of the reactants with the acrylic polymer.

The optimum condition will depend on the particular reactants used and the degree of reaction desired. The exact condition can be determined by simple
20 experimentation.

The imidization reaction can be enhanced by conducting the reaction in the presence of a basic catalyst, an acid catalyst and/or a transamination catalyst. Such catalysts may be selected from a tertiary
25 amine, such as dicyclohexylamine, 1,1,3,3-tetramethylguanidine, 1,3-diphenylguanidine, quinoline, isoquinoline, 4-benzylpyridine, 4-phenylpyridine, 2,3-benzodiazine, 1,4-benzodiazine, 1-benzazine, 1,3-benzodiazine, N,N'-dicyclohexylcarbodiimide, 2,2'-
30 bipyridyl, 2,3'-bipyridyl, 2,4'-bipyridyl or such catalyst can be selected from the group consisting of p-toluenesulfonic acid, HCl, Sb₂O₃, Ti-(OC₄H₉)₄, NaNH₂, SnO₂, potassium or sodium alkoxides, manganese acetate, and the

- 11 -

like. The catalyst can be present in amounts of from 0.1 to 5 weight percent based on the amine reactant.

The reactants are contacted with each other at the above described reaction conditions for from about 1 to 8 hours and preferably from about 1.5 to 3 hours. When a two-stage process is conducted, the first stage is carried out for 1 to 2 hours and then, with reduction in temperature, the second stage is carried out for 1 to 3 additional hours. During the course of the reaction, water (a by-product) is removed to drive the reaction to imidization. When the reaction is carried out at ambient or substantially ambient pressure, the removal of water can be enhanced by sweeping a gas, such as nitrogen, through the reaction zone.

The degree of reaction can be substantially monitored by the amount of water removed from the reaction zone. Upon completion of the reaction, the reaction product is cooled, filtered and, optionally, neutralized with an aqueous alkali or alkaline earth metal base.

The imidized acrylic polymer is normally a high-boiling viscous liquid which is substantially soluble in water. In most instances, the polymer is soluble in all proportions.

The improved cement of the present invention is composed of a substantially uniform mixture of the hydraulic cement and the imidized acrylic polymer which are both described herein above. The imidized acrylic polymer should be present in from 0.005 to 5 (preferably from 0.03 to 1 and most preferably from 0.05 to 0.3) weight percent based on the weight of hydraulic cement. In order to aid in forming the uniform mixture, the imidized acrylic polymer can be mixed with the cement as

- 12 -

an aqueous solution having from about 30 to 50 weight percent imidized acrylic polymer solids in the solution.

The imidized acrylic polymer treated cement can be formed at any stage of the cement's formation or use.

5 For example, the polymer can be mixed at the cement mill with clinker cement raw material during its grinding to form cement powder. It can also be applied to the cement powder during its blending with other dry materials to prepare a specific type of cement, such as blended
10 cement, pozzolanic cement and the like.

Alternately, the improved cement can be formed in situ during the course of preparing a cement composition such as a mortar mix (hydraulic cement, sand and water) or a concrete (hydraulic cement, sand, large aggregate,
15 such as stone, and water). The subject imidized polymer can be added (conventionally as an aqueous solution) as part of the water of hydration or can be added separately. In the later method of application, the water of the aqueous polymer solution should be
20 calculated as part of the total water content of the cement composition.

As stated above, the imidized acrylic polymer of the improved cement (whether as a dry blend of cement and polymer or as formed in situ as part of the formation of
25 a wet unset cement composition) should be from 0.005 to 5, preferably from 0.03 to 1 and most preferably from 0.05 to 0.3 weight percent of solid imidized acrylic polymer based on the weight of solid hydraulic cement of the cement composition.

30 Cement compositions formed with the present improved cement have a significantly higher degree of flowability (higher degree of slump), than compositions formed with conventional hydraulic cement. Further, the present

- 13 -

5 cement compositions are capable of retaining their high degree of slump over a sustained period of time giving the artisan an extended period to work the cement composition into its final shape. Finally, the present cement composition achieves initial set without exhibiting excessive retardation. Thus, the use of this cement composition does not cause delay of the working time required to form a particular structure.

10 Conventional cement additives, such as air entrainers, water proofing agents, strength enhancers, corrosion inhibitors, antifoaming agents and curing accelerators can be used with the subject cement additive. These additives can be mixed with the cement composition prior to, along with or subsequent to the addition of the present cement additive.

15 The present invention is further explained by the following examples which are given for illustrative purposes only and are not meant to limit the invention, as defined by the claims, appended hereto. All parts and percentages are by weight unless otherwise stated.

EXAMPLES

Example 1

25 40 parts of solid polyacrylic acid of 5000 molecular weight was added to 60 parts of a polyethylene - polypropylene oxide polymer of molecular weight 700 which is terminated at one end with a primary amine group and at the other end by a methyl group. The reaction mixture was stirred for 30 minutes at ambient temperature followed by 1 hour and 10 minutes at 180°C under a blanket of flowing nitrogen gas. The water by-product was

30

- 14 -

removed in the nitrogen gas stream. The resultant product was a viscous amber liquid. The liquid was analyzed by infrared spectroscopy and the resultant spectra had peaks at 1720 cm^{-1} , 1630 cm^{-1} , and 750 cm^{-1} which indicates the presence of imide groups. This liquid was also analyzed by conductimetric titration and the nitrogen linkages were found to have an 4:1 amide:imide group ratio.

Example 2

7.5 parts of solid polyacrylic acid of 2000 molecular weight was dissolved in 7.7 parts deionized water. To this resultant solution was added 52.1 parts of a polyethylene-polypropylene oxide polymer of molecular weight 2000 which was terminated at one end by a primary amine group and at the other end by a methyl group. The mixture was heated and maintained at 180°C under a flowing nitrogen gas blanket for a total of 2 hours to remove the water of solution and that formed as a reaction by-product. The resulting product was an amber viscous liquid.

Example 3

25 parts of a 50% aqueous solution of a polyacrylic acid of 5000 molecular weight was combined with 52 parts of a polyethylene-polypropylene oxide polymer of molecular weight 2000 which was terminated at one end by a primary amine group and at the other end by a methyl group. The mixture was heated and maintained at 180°C while under flowing nitrogen gas stream for a total of 2 hours. The water of solution and formed as by-product

- 15 -

was removed in the nitrogen gas stream. The resulting product was an amber viscous liquid.

Example 4

5 30 parts of a 65% aqueous solution of a polyacrylic acid of 2000 molecular weight was mixed with 29.3 parts of a (polyethylene-polypropylene) oxide polymer of molecular weight 700 which was terminated at one end by a primary amine group and at the other end by a methyl group. The mixture was heated under flowing blanket of
10 nitrogen gas at 180°C for 1 hour and 30 minutes. The water of the solution and from the reaction was removed by the nitrogen gas stream. The resulting product was an amber viscous liquid.

Example 5

15 19.2 parts of a 65% aqueous solution of a polyacrylic acid of 2000 molecular weight was combined with 3.0 parts of 30% aqueous solution of ammonia. To the solution was then added 48 parts of a polyethylene-polypropylene oxide polymer of molecular weight 700 which
20 was terminated at one end by a primary amine group and at the other end by a methyl group. The mixture was heated and maintained at 180°C while under flowing nitrogen gas stream for a total of 30 minutes. The water of the solution and that formed as a by-product was removed in
25 the nitrogen stream. A yellow creamy liquid was isolated as the product and was determined to contain both reacted ammonia and alkoxyamine groups.

- 16 -

Example 6

154 parts of a 50% solution in water of polyacrylic acid of 2000 molecular weight was added to 312 parts of a polyethylene-polypropylene oxide polymer of molecular weight 2000 which was terminated at one end by a primary amine group at the other end by a methyl group. The mixture was heated and maintained at 180°C under flowing nitrogen gas stream for a total of 7 hours until substantially all of the water was removed. The resulting product was an amber viscous liquid.

Example 7

5.2 parts of a polymethacrylic acid of molecular weight 3400 was dissolved in 8.2 parts of distilled water. After 45 minutes, the polymethacrylic acid was completely dissolved and 18.0 parts of a polyethylene-polypropylene oxide polymer of molecular weight 2000 terminated at one end by a primary amine and terminated at the other end by a methyl group was added. The mixture was stirred at room temperature for 30 minutes. Heat was applied at 180°C under flowing nitrogen for 1 hour. The resulting product was an amber viscous liquid.

A sample of the resultant imidized acrylic polymer was tested as part of an ordinary portland cement mortar in a method based on Japanese Industrial Standard (JIS) A6204. A sand/cement/water ratio of 1/3/0.50 was used with the polymer dissolved in the water to give a dosage of 0.15% solid polymer based on solid cement (s/s). In order to eliminate the effects of air on the flow of the mortar, a commercial defoamer was employed at 20-30 ppm based on the weight of cement. Set times were measured

- 17 -

using an automated penetrometer on a sample formed using 0.20% s/s dosage of polymer. Results of these tests are given in Table 3 below.

Example 8

5 Each of the formed imidized acrylic polymers of Examples 1,3,4,5 and 6 were formed into 50% aqueous solutions with deionized water. Each of the solutions was used in forming a cement composition composed of standard hydraulic portland cement and water. The
10 polymer to cement weight ratio (solid polymer/solid cement, s/s) was 0.002 and the water to cement ratio was 0.5. A miniature slump test developed by Kantro as described in "Cement, Concrete and Aggregates" Vol. 2, No. 2, Page 95 1980 was used to measure slump of each
15 sample. Set was measured by an automated penetrometer. The results for samples of Examples 2-6 are given in Table 1 below. Further, samples of a concrete cement composition were treated with the imidized acrylic polymer of Example 6 and, for comparative purposes, with
20 a conventional concrete superplasticizing agent, naphthalene sulfonate formaldehyde condensate ("NSFC"), in dosages set forth in Table 2 below. The concrete mix design was composed of: portland cement at a rate of 600 lbs/yd³; sand at a rate of 1400 lbs/yd³; coarse aggregate
25 (crushed stone) at a rate of 1700 lbs/yd³ and water (including from admixture) in 300 lbs/yd³. These samples and a blank were tested according to ASTM C143 for slump, ASTM C403 for set, and ASTM C39 for compressive strength. A commercial defoamer was also incorporated to eliminate
30 air effects on slump and compressive strength. The results of these tests are given in Table 2 below.

Table 1 - Cement Paste Results

Minislump spread (cm)

Preparation	Dosage (% s/s)	9 min.	18 min.	30 min.	45 min.	60 min.	Set time (min.)
Blank	---	14.9	13.9	12.6	10.9	10.0	187
Example 2	0.2	19.8	20.4	20.0	19.3	18.3	327
Example 3	0.2	20.7	24.4	22.3	20.4	18.4	334
Example 4	0.2	18.1	18.5	18.8	17.5	16.5	342
Example 5	0.2	18.7	20.2	17.6	17.5	16.6	288
Example 6	0.2	21.6	20.9	22.0	18.9	18.9	287

SUBSTITUTE SHEET (RULE 26)

Table 2 - Concrete Results

Preparation	Dosage	Slump				Set	Compressive Strength		
		(% s/s)	(in. at 9 min.)	(in. at 18 min.)	(in. at 30 min.)	(in. at 45 min.)	1 day (psi)	7 day (psi)	28 day (psi)
Blank	---		2.75	NM	NM		1782	5140	6097
Example 6	0.125		8.00	7.25	5.25	3.00	2012	5182	6442
NSFC	1.00		8.00	5.50	3.25	2.50	1683	3641	5872

SUBSTITUTE SHEET (RULE 26)

The results of Table 2 clearly show that the present imidized acrylic polymer admixture containing cement composition provides a high initial slump, retains a high slump over a sustained period, has substantially no set retardation and exhibits enhanced compressive strength when compared to the untreated cement composition and to a cement composition containing a conventional superplasticizer, NSFC.

5

Table 3 - Mortar Flow Results

Preparation	Flow				Set ¹ (hr:min)
	Dosage (%s/s)	4 min. (mm)	30 min. (mm)	60 min. (mm)	
Blank	---	105	NM	NM	5:00
Example 7	0.15	220	197	163	5:30

¹Set measured at 0.20% s/s of Example 7.

Example 9Polymer Admixture Product

A. 20 parts of a polyacrylic acid powder having a number average molecular weight of 2000 was mixed with 40 parts of a commercially available methoxy terminated polyoxyethylene amine (Jeffarmine M-2070) of a weight average molecular weight of 2000 and 80 parts of a methoxy terminated polyoxyethylene amine (Jeffarmine M-1000) having a weight average molecular weight of 1000. The mixture was formed in a reactor equipped with a mechanical stirrer, a nitrogen gas inlet and a condenser equipped with a Dean-Stark trap. The mixture was slowly heated to 70°C under a nitrogen gas flow. Upon attaining 70°C, 21 parts of dicyclohexylcarbodiimide was added and the mixture was maintained at 70°C for 4 hours. The reaction product was cooled to ambient conditions and neutralized with aqueous sodium hydroxide solution and filtered. Then an aqueous solution containing forty percent solid neutralized product was formed by the addition of water.

B. The process described in A above was repeated except that an aqueous solution containing 40f a pol parts of the solid polyacrylic acid was used instead of the powder material. The mixture was initially heated to 120°C with water removal. When the water attributable to the polymer solution initially added was removed, 0.2 part of p-toluene sulfonic acid was introduced into the reaction mixture instead of carbodiimide and the mixture was maintained at 120°C

- 23 -

for 4 hours. The resultant product was a viscous oil which was neutralized and the aqueous solution was labeled Product B.

5 C. The process described in A above was repeated
except that an aqueous solution containing 40 parts
of the polyacrylic acid was used instead of the
powder material. The polyacrylic acid was mixed
with 40 parts Jeffamine M-2070, 20 parts Jeffamine
10 M-1000 and 0.87 part morpholine. Water was
initially distilled off at 180°C for 2 hours and
then the temperature was reduced to 120°C, 0.58 part
p-toluene sulfonic acid was added and the reaction
was continued for two (2) hours more. The resultant
15 product was a viscous yellow oil which was
neutralized and its aqueous solution was labeled
Product C.

20 D. The process described in A above was repeated
except that an aqueous solution containing 40 parts
of polyacrylic acid was used instead of the powder
material. This was mixed with 80 parts Jeffamine M-
1000 at 170°C for 2 hours with removal of water and
then reduced to 120°C, 0.5 part p-toluenesulfonic
acid added and further mixed for two (2) hours. The
25 resultant product was a viscous oil which was
neutralized and its aqueous solution was labelled
Product D.

E. The process described in D above was repeated
except 80 parts of polyacrylic acid (as aqueous
solution) was mixed with 180 parts Jeffamine M-1000.

- 24 -

The reaction mixture was maintained at 170°C for 2.5 hours. No p-toluenesulfonic acid was added. The

product was a viscous oil which was neutralized and the aqueous solution was labelled Product E.

5 F. A process described in A above was repeated
 using 20 parts polyacrylic acid powder, 10 parts
 Jeffamine M-2070 and 80 parts of a commercially
 available polyethylene ether/propylene ether glycol
10 having one end terminated with a methoxy group, and
 having a weight average molecular weight of 2000.
 The reaction was initially carried out at 110°C for
 1 hour after which p-toluenesulfonic acid was added
 and the reaction was continued for 2 more hours.
 The product was a viscous yellow oil which was
15 neutralized and made into an aqueous solution
 labelled Product F.

 G. A process described in D above was repeated
 except that 76 parts of Jeffamine M-2070 was used
 instead of Jeffamine M-1000. In addition, 0.9 part
20 of a difunctional poly(oxyethylene)(oxypropylene)
 copolymer having terminal primary amine groups
 (Jeffamine ED-900), weight average molecular weight
 of 900 and a propylene/ethylene mole ratio of 2.5 to
 15.5 was also introduced into the reaction mixture.
25 The mixture was heated at 170°C for four (4) hours
 under a partial vacuum. The product was a viscous
 oil product which was neutralized and made into an
 aqueous solution labelled Product G.

- 25 -

H. The process described in G above was repeated except that four (4) parts of Jeffamine ED-2000 was used instead of Jeffamine ED-900. Jeffamine ED-2000 is a poly(oxyethylene)oxypropylene) copolymer having terminal primary amine groups, a weight average molecular weight of 2000, and a propylene/ethylene mole ratio of 2.5/40.5. The product was a viscous oil which was neutralized and made into aqueous solution labelled Product H.

Example 10

Concrete Admixture

Each of the polymer solutions A - H of Example 9 above was used in formulating concrete samples which were tested for slump, air content set time, and compressive strength. All samples were formed according to a modified ASTM C-1017-92. The parts of portland cement was 611 parts; of sand was 1700 parts; of gravel was 1359 parts and water was 285. The water to cement ratio was 0.47. The subject additive was employed with a commercial defoamer for cement. The dosages (S/S = solid additive based on solid portland cement of concrete composition) are listed in Table 4 below and tabulated with respect to the results of the test for each of the samples produced.

The concrete samples were not all formed at the same time. Therefore, a blank was formed for each of the tests to provide a more accurate determination of the effects of the admixture versus a blank. The results shown in the table below give values for test sample/blank sample. The slump was measured by ASTM C-143; air by ASTM C-231; and compressive strength by ASTM C-39 and set time by ASTM C-403.

- 26 -

Table 4

Admixture Product	Dosage % S/S	Other Additive	Dosage % S/S 10 ⁻³	Slump Inch @ 9 min	Air %	Initial Set h:min/h:min Blank	Compressive Strength PSI	
							7 days	28 days
A	0.125	Defoamer	225	8.0/2.7	3.5	6:19/5:04	5374/5340	7305/7128
B	0.14	Defoamer	225	5.3/2.9	2.5	6:20/4:52	4363/4525	6140/6380
C	0.12	Defoamer	200	9.1/3.1	1.8	5:56/4:06	5009/4764	6070/6391
D	0.08	Defoamer	200	8.5/2.7	2.3	6:01/4:53	5315/5517	6900/6904
E	0.08	Defoamer	200	8.5/2.9	2.6	4:33/4:06	5348/5111	-----
F	0.12	Defoamer	200	5.1/3.1	2.7	4:31/4:06	4908/4764	6145/6391
G/E	0.06/0.06	Defoamer	200	8.5/2.8	2.8	5:08/4:08	5833/6112	-----
H/E	0.06/0.06	Defoamer	200	7.2/2.8	3.1	5:18/4:08	5983/6112	-----

5

10


- 27 -

All of the above samples illustrated that the subject polymer product provided a combination of high slump characteristics, without causing excessive increase in initial set or adversely effecting compressive strength of the concrete formed.

5

What is Claimed:

1. An improved cement comprising a substantially uniform mixture of a hydraulic cement and from 0.01 to 2 weight percent based on the weight of said hydraulic cement of an imidized acrylic polymer represented by the structure of:



wherein each R independently represents hydrogen atom or a methyl (CH₃-) group; R' represents a hydrogen atom or a C₂-C₁₀ oxyalkylene group represented by (BO)_nR'' in which O represents an oxygen atom, B represent C₂-C₁₀ alkylene group or mixtures thereof, R'' represents a C₁-C₁₀ alkyl and n represents an integer of from 1-200, or mixtures thereof; A represents hydrogen atom, a C₁-C₁₀ alkyl group, R' or an alkali metal alkaline earth or ammonium cation or a mixture thereof; NR''' represents a heterocyclic group of which N is a part thereof; and a, b, c, d and e are numerical values representing molar percentage of the polymers structure such that a is a value of about 50 to 90; the sum of c + d is a value of from about 2 to the numerical value of [100 - (a+b)]; and b is a remainder value of [100 - (a+c+d+e)]; and e is a value of from 0 to about 0 to 10.


2. The improved cement of Claim 1 wherein R' represents an oxyalkylene group, (BO)_nR'' wherein B is a C₂ - C₃ alkylene group or mixtures thereof; R'' is a C₁ - C₃ alkyl group; and n is an integer of from 1 to 70.

- 29 -

3. The improved cement of Claim 1 wherein R' represents hydrogen atom.

4. The improved cement of Claim 2 wherein at least a portion of A represents an oxyalkylene group $(BO)_nR''$ wherein B is a $C_2 - C_3$ alkylene group or mixtures thereof; R'' is a $C_1 - C_3$ alkyl group; and n is an integer of from 1 to 70.

5. An imidized acrylic polymer represented by the structural formula:



wherein each R independently represents hydrogen atom or a methyl (CH_3-) group; R' represents a hydrogen atom or a C_2-C_{10} oxyalkylene group represented by $(BO)_nR''$ in which O represents an oxygen atom, B represents a C_2-C_{10} alkylene group or mixtures thereof, R'' represents a C_1-C_{10} alkyl and n represents an integer of from 1-200, or mixtures thereof; A represents hydrogen atom, a C_1-C_{10} alkyl group, R' or an alkali metal, alkaline earth metal or ammonium cation or a mixture thereof; NR''' represents a heterocyclic group of which N is a part thereof; and a, b, c, d, and e are numerical values representing molar percentage of the polymers structure such that a is a value of about 50 to 90; the sum of c + d is a value of from about 2 to the numerical value of $[100 - (a+b)]$; and

b is a remainder value of $[100 - (a+c+d+e)]$; and e is a value of from 0 to 10.

5 6. The polymer of Claim 5 wherein R' represents an oxyalkylene group, $(BO)_nR''$ wherein B is a $C_2 - C_3$ alkylene group or mixtures thereof; R'' is a $C_1 - C_3$ alkyl group; and n is an integer of from 1 to 70.

 7. The polymer of Claim 5 wherein R' represents hydrogen atom.

10 8. The polymer of Claim 6 wherein at least a portion of A represents an oxyalkylene group $(BO)_nR''$ wherein B is a $C_2 - C_3$ alkylene group or mixtures thereof; R'' is a $C_1 - C_3$ alkyl group; and n is an integer of from 1 to 70.

15 9. A process of forming an imidized polymer comprising contacting a polymer having carboxylic acid groups, their $C_1 - C_{10}$ alkyl esters and mixtures thereof positioned pendant alpha-beta, alpha-gamma or both from the polymer backbone chain with an amine selected from ammonia or a primary amine reactant of the formula



 wherein O represents oxygen atom, B represents a $C_2 - C_{10}$ alkylene group, R'' represents a $C_1 - C_{10}$ alkyl group, and n represents an integer of 1 to 200; maintaining said reaction mixture at a temperature of from 60 to 250°C at
25 atmospheric or reduced atmospheric pressure for a time of from 1 to 8 hours while removing water from the reaction mixture; and cooling and recovering the formed imidized polymer product.

- 31 -

10. The process of Claim 9 wherein the polymer is a polyacrylic acid or ester thereof and the primary amine reactant is of the formula $H_2N(BO)_nR''$.

5 11. The process of Claim 10 wherein the polymer reactant and primary amine reactant are further contacted with reactants selected from a hydroxy terminated oxyalkylene compound of the formula $HO(BO)_nR''$ wherein O, B and R'' each is defined above, or a secondary amine HNR''' , wherein R''' is a heterocyclic group of which N
10 is a part thereof or mixtures of said reactants.

12. The process of Claim 10 wherein the reactants are maintained at a temperature of about 150 to 225°C for a period of from 1.5 to 3 hours.

15 13. The process of Claim 10 wherein the reactants are maintained at a temperature of at least about 60°C in the presence of a catalyst selected from an acid catalyst, basic catalyst or transamination catalyst.

20 14. The process of Claim 11 wherein the reactants are first maintained at a temperature of from 150 to 225°C for a period of from about 1 to 2 hours and subsequently maintained at a temperature of at least 75°C in the presence of a catalyst selected from an acid catalyst, basic catalyst or transamination catalyst for a period of 1 to 3 hours.

25 15. The process of Claim 10 wherein the polymer reactant and primary amine reactant are further contacted with a reactant selected from difunctional amino or hydroxyl terminated compounds of the formula $Z(BO)_nZ$

wherein Z represents a primary amino or hydroxyl group and B, O and n represent that of the primary amine reactant.

5 16. The process of Claim 11 wherein the polymer reactant and primary amine reactant are further contacted with a reactant selected from difunctional amino or hydroxyl terminated compounds of the formula $Z(BO)_nZ$ wherein Z represents a primary amino or hydroxyl group and B, O and n represent that of the primary amine
10 reactant.

 17. A polymer product useful as a cement admixture, said product formed according to the process of Claim 9 comprising contacting a polymer having carboxylic acid groups, their $C_1 - C_{10}$ alkyl esters and mixtures thereof
15 positioned pendant alpha-beta, alpha-gamma or both from the polymer backbone chain with an amine selected from ammonia or a primary amine reactant of the formula



 wherein O represents oxygen atom, B represents a $C_2 - C_{10}$ alkylene group, R'' represents a $C_1 - C_{10}$ alkyl group, and
20 n represents an integer of 1 to 200; maintaining said reaction mixture at a temperature of from 75 to 250°C at atmospheric or reduced atmospheric pressure for a time of from 1 to 8 hours while removing water from the reaction
25 mixture; and cooling and recovering the formed imidized polymer product.

 18. A polymer product useful as a cement admixture, said product formed according to the process of Claim 10 wherein the polymer is a polyacrylic acid or ester

- 33 -

thereof and the primary amine reactant is of the formula $H_2N(BO)_nR''$.

19. A polymer product useful as a cement admixture, said product formed according to the process of Claim 11 wherein the polymer reactant and primary amine reactant are further contacted with a reactant selected from a hydroxy terminated oxyalkylene compound of the formula $HO(BO)_nR''$ wherein O, B and R'' each is defined above, or a secondary amine HNR''' , wherein R''' is a heterocyclic group of which N is a part thereof.

20. A polymer product useful as a cement admixture, said product formed according to the process of Claim 12 wherein the reactants are maintained at a temperature of about 150 to 225°C for a period of from 1.5 to 3 hours.

21. A polymer product useful as a cement admixture, said product formed according to the process of Claim 13 wherein the reactants are maintained at a temperature of at least about 75°C in the presence of a catalyst selected from an acid catalyst, basic catalyst or transamination catalyst.

22. A polymer product useful as a cement admixture, said product formed according to the process of Claim 14 wherein the reactants are first maintained at a temperature of from 150 to 225°C for a period of from about 1 to 2 hours and subsequently maintained at a temperature of at least 75°C in the presence of a catalyst selected from an acid catalyst, basic catalyst or transamination catalyst for a period of 1 to 3 hours.

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C04B 24/26, C08F 8/30, 8/48	A3	(11) International Publication Number: WO 95/09821	(43) International Publication Date: 13 April 1995 (13.04.95)
--	----	---	--

(21) International Application Number: PCT/US94/10134

(22) International Filing Date: 13 September 1994 (13.09.94)

(30) Priority Data:

08/128,939

29 September 1993 (29.09.93)

US

08/299,028

6 September 1994 (06.09.94)

US

(71) Applicant: W.R. GRACE & CO.-CONN. [US/US]; 1114
Avenue of the Americas, New York, NY 10035 (US).(72) Inventors: ARFAEI, Ahmad; 72 Stonegate Road, Chelmsford,
MA 01824-4153 (US). DARWIN, David, Charles; 9009
Blue Pool, Columbia, MD 21045 (US). GARTNER, Ellis,
Martin; 1105 Tanley Road, Silver Spring, MD 20904 (US).
CHUN, Byong-Wa; 3-22-6 Kirigaoka #306, Midori-ku,
Yokohama, Kanagawa 227 (JP). KOYATA, Hideo; 4-2-1
Ryokuen #2-105, Izumi-ku, Yokohama, Kanagawa 245 (JP).
KUO, Lawrence, Lu; 8592 Dark Hawk Circle, Columbia,
MD 21045 (US).(74) Agent: TROFFKIN, Howard, J.; W.R. Grace & Co.-Conn.,
7379 Route 32, Columbia, MD 21044 (US).(81) Designated States: AM, AT, AU, BB, BG, BR, BY, CA, CH,
CN, CZ, DE, DK, EE, ES, FI, GB, GE, HU, JP, KE, KG,
KP, KR, KZ, LK, LR, LT, LU, LV, MD, MG, MN, MW,
NL, NO, NZ, PL, PT, RO, RU, SD, SE, SI, SK, TJ, TT,
UA, UZ, VN, European patent (AT, BE, CH, DE, DK, ES,
FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent
(BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD,
TG), ARIPO patent (KE, MW, SD).**Published***With international search report.**Before the expiration of the time limit for amending the
claims and to be republished in the event of the receipt of
amendments.*(88) Date of publication of the international search report:
4 May 1995 (04.05.95)(54) Title: IMPROVED CEMENT ADMIXTURE PRODUCT HAVING IMPROVED RHEOLOGICAL PROPERTIES AND PROCESS
OF FORMING SAME

(57) Abstract

The present invention is directed to an imidized polycarboxylic acid polymer useful as a cement admixture, to improved cement compositions containing said polymer and to a process of forming the same.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 C04B24/26 C08F8/30 C08F8/48

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C04B C08F C08G

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP,A,0 448 717 (NIPPON SHOKUBAI KAGAKU KOGYO CO. LTD.) 2 October 1991 see claims 1-27 ---	1
A	DE,A,40 34 708 (SANDOZ-PATENT-GMBH) 8 May 1991 see claims 1-8 ---	1
A	EP,A,0 056 627 (NIPPON SHOKUBAI KAGAKU KOGYO CO., LTD.) 28 July 1982 cited in the application see claims 1-24 ---	1
A	EP,A,0 300 760 (MITSUBISHI RAYON CO., LTD.) 25 January 1989 see claims 1-9 ---	5
	--- -/--	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

- * "A" document defining the general state of the art which is not considered to be of particular relevance
- * "E" earlier document but published on or after the international filing date
- * "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- * "O" document referring to an oral disclosure, use, exhibition or other means
- * "P" document published prior to the international filing date but later than the priority date claimed

- * "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- * "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- * "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- * "A" document member of the same patent family

Date of the actual completion of the international search

16 March 1995

Date of mailing of the international search report

29. 03. 95

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2230 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax (+31-70) 340-3016

Authorized officer

Permentier, W

DOCUMENTS CONSIDERED TO BE RELEVANT		
Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	PATENT ABSTRACTS OF JAPAN vol. 12, no. 223 (C-507) (3070) 24 June 1988 & JP,A,63 020 303 (NIPPON SHOKUBAI KAGAKU KOGYO CO., LTD.) 28 January 1988 see abstract ---	9
A	WO,A,92 07010 (METZGER) 30 April 1992 see claims 1-19 ---	9
A	FR,A,2 224 498 (SANDOZ S.A.) 31 October 1974 see claims 1-29 ---	9
A	GB,A,879 950 (UCC) 11 October 1961 see claims 1-55 ---	9
A	FR,A,2 470 140 (PPG INDUSTRIES, INC.) 29 May 1981 see claims 1-34 -----	9

Form PCT/ISA/210 (continuation of second sheet) (July 1992)

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP-A-0448717	02-10-91	CA-A- 2037058 WO-A- 9101282	26-01-91 07-02-91
DE-A-4034708	08-05-91	JP-A- 3150243 AT-A- 222590 AU-B- 639034 AU-A- 6584890 BE-A- 1005160 CA-A- 2029309 CH-A- 680289 FR-A- 2656297 GB-A, B 2237808 US-A- 5358566	26-06-91 15-06-94 15-07-93 09-05-91 11-05-93 07-05-91 31-07-92 28-06-91 15-05-91 25-10-94
EP-A-0056627	28-07-82	JP-C- 1204259 JP-A- 57118058 JP-B- 58038380 JP-C- 1241485 JP-A- 57119896 JP-B- 59016519 JP-C- 1204261 JP-A- 58032051 JP-B- 58038381 JP-C- 1239029 JP-A- 58006295 JP-B- 59014277 US-A- 4471100	25-04-84 22-07-82 23-08-83 26-11-84 26-07-82 16-04-84 25-04-84 24-02-83 23-08-83 13-11-84 13-01-83 03-04-84 11-09-84
EP-A-0300760	25-01-89	JP-A- 1022903 JP-C- 1817810 JP-B- 3002441 AU-B- 602994 DE-D- 3852850 US-A- 4940778	25-01-89 27-01-94 16-01-91 01-11-90 09-03-95 10-07-90
WO-A-9207010	30-04-92	EP-A- 0553189 JP-T- 6502207	04-08-93 10-03-94
FR-A-2224498	31-10-74	CH-A- 596244 DE-A- 2416022	15-03-78 24-10-74

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
FR-A-2224498		GB-A- 1467156	16-03-77
		JP-A- 50052199	09-05-75
		US-A- 3980682	14-09-76

GB-A-879950		BE-A- 571756	
		CH-A- 392068	
		DE-B- 1100950	
		FR-A- 1204449	26-01-60
		NL-C- 111374	
		NL-A- 226509	

FR-A-2470140	29-05-81	US-A- 4285849	25-08-81
		AU-B- 523434	29-07-82
		AU-A- 6352080	04-06-81
		CA-A- 1148296	14-06-83
		DE-A,C 3043355	29-10-81
		GB-A,B 2067202	22-07-81
		JP-B- 1036865	02-08-89
		JP-C- 1553252	04-04-90
		JP-A- 61062569	31-03-86
		JP-C- 1412460	27-11-87
		JP-A- 57115403	17-07-82
		JP-B- 62017601	18-04-87
